

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 89103574.3

(51) Int. Cl. 4: D21H 1/22

(22) Date of filing: 01.03.89

(30) Priority: 02.03.88 JP 47496/88
 02.03.88 JP 47497/88
 02.03.88 JP 47498/88
 02.03.88 JP 47499/88
 02.03.88 JP 47500/88

(43) Date of publication of application:
 06.09.89 Bulletin 89/36

(84) Designated Contracting States:
 DE FR GB

(71) Applicant: MITSUI TOATSU CHEMICALS INC.
 No. 2-5, Kasumigaseki 3-chome
 Chiyoda-Ku Tokyo 100(JP)

Applicant: OJI PAPER COMPANY LIMITED
 7-5 Ginza 4-Chome Chuo-ku
 Tokyo(JP)

(72) Inventor: Kaneda, Katsumi
 1120, Higashimatano-cho Totsuka-ku

Yokohama-shi Kanagawa(JP)
 Inventor: Hyugaji, Teruo
 3-14-14 Shodo Sakae-ku
 Yokohama-shi Kanagawa(JP)
 Inventor: Tanaka, Akio
 21-12, Kamino-cho Sakae-ku
 Yokohama-shi Kanagawa(JP)
 Inventor: Kuroda, Nobuo
 1500, Kuzumo
 Yonago-shi Tottori(JP)
 Inventor: Yamamoto, Itsuro
 2-20, Tatemachi
 Yonago-shi Tottori(JP)
 Inventor: Matsuda, Noriaki
 97-26, Abe
 Yonago-shi Tottori(JP)

(74) Representative: Strehl, Schübel-Hopf,
 Groening, Schulz
 Maximilianstrasse 54 Postfach 22 14 55
 D-8000 München 22(DE)

(54) Coating composition and cast-coated paper coated with same.

(57) A coating composition for a cast-coated paper which principally comprises a pigment and an adhesive and in which the adhesive is composed of (A) a rubber latex having an average particle size of 0.1 to 0.3 micron and (B) a rubber latex or an acrylic emulsion having an average particle size of 0.5 to 1.5 micron and the sum of the solid content of the components (A) and (B) is in the range of 9 to 30 parts by weight per 100 parts by weight of the pigment is herein provided. The coating composition may further contain casein as a binder. In addition, inorganic compounds selected from NaCl, Na₂SO₄, ZnO and MgO and organic acid salts selected from formates or acetates of Ca, Zn, Mg may be added to the coating composition as coagulants. The use of the aforesaid coating composition makes it possible to produce cast-coated paper having excellent permeability, gloss and surface strength at a high speed.

EP 0 331 143 A2

COATING COMPOSITION AND CAST-COATED PAPER COATED WITH THE SAME

BACKGROUND OF THE INVENTION

5 The present invention relates to a coating composition suitable for cast-coated paper capable of being produced at a high speed and the cast-coated paper coated with such a coating composition.

There have been known various methods for manufacturing a cast-coated paper, such as wet cast coating, gel cast coating and rewet cast coating techniques. The wet cast coating is a method which comprises applying a water-based paint containing a pigment and an adhesive to a base paper and directly drying the paper still in wet state by bringing it into contact with a highly heated mirror drum (hereunder
10 referred to as "cast drum"). The gel cast coating is a method which comprises adding a coagulant to the water-based paint, applying the water-based paint to a base paper and bringing the paper still in wet state into contact with the cast drum to dry the same, or a method which comprises applying the water-based paint to base paper, coating a coagulant onto the paper and then bringing the paper still in wet state into contact with the cast drum to dry the same. Furthermore, the rewet cast coating is a method which
15 comprises the steps of applying a water-based paint to a base paper, drying the paper and again wetting it prior to bringing it into contact with the cast drum to dry it. Art paper of high gloss is supercalendered in its dry state, but the cast-coated paper is made smooth while it is still in wet state in other words while the coated layer is still in highly plastic state, in either of these cast coating techniques. Therefore, according to the cast coating technique, a coated surface of high gloss and high smoothness can be obtained.

20 However, it is of primary importance to release the coated paper from the surface of the cast drum without any trouble after bringing the coated surface containing a great amount of water into contact with the cast drum to dry the same, in order to obtain a coated paper surface having high gloss and free of defects. It has been known that good adhesion to the cast drum surface which is an essential requirement for imparting high gloss to the cast-coated paper leads to substantial reduction in the releasability thereof.
25 Therefore, manufacture of the cast-coated paper having high gloss and substantially free from defects of the coated surface such as pinholes requires an advanced technology. In particular, as the speed of releasing the coated paper from the cast drum is increased to achieve high-speed operation, the resistance encountered during releasing is also increased, the coated film on the paper adheres to the surface of the cast drum and as a result, a partial pick-up of the paper is sometimes observed (hereunder the such
30 defects of the coated paper surface are referred to as "pit(s)"). Accordingly, it is very difficult to obtain a coated paper having uniform gloss and free of defect. Moreover, it is in general required to quickly evaporate moisture of the coated paper on the drum, but when the machine is operated at high speed, the residence time of the coated paper on the drum is reduced and, therefore, strong drying conditions must be employed to enhance the mobility of vapour. As a result, a novel problem arises. In other words, in the
35 wet cast coating the paint causes boiling which leads to destruction of the coated layer and in the gel cast coating, it becomes difficult to transfer a large amount of water in the gelled coated layer to the base paper, which in turn makes it difficult to hence form a uniform surface. Particularly, in the rewet cast coating, since the coated layer once dried is rewetted to impart plasticity thereto, a rather high pressure should be applied to the coated paper on the drum as compared with the foregoing two cast coating techniques. As a result,
40 small water pools are often formed between the drum surface and the coated film, but sufficient removal thereof through voids of the coated film is quite difficult. This leads to the formation of pits differing from those formed due to pick-up and provides a cast coated paper having a large number of defects.

In order to solve these problems associated with the cast-coated paper as much as possible and to make a high speed production possible while maintaining the quality of coated paper surface, there has
45 been proposed a method in which a coagulant such as a sulfate, nitrate, formate or acetate of a metal such as zinc, aluminum or magnesium is incorporated into a paint principally composed of a pigment and an adhesive such as a latex containing a polymer having repeating units derived from an unsaturated carboxylic acid as a functional monomer or casein (see Japanese Patent Publication No. 60-146097). This article states that metal ions of the coagulant used affect the carboxyl groups of the copolymeric latex to
50 cause coagulation during drying of the coated layer to thus make the coated layer porous and that the porous structure of the coated paper makes the permeation of evaporated moisture easy when the coated paper is rewetted and pressed to the heated cast drum according to the rewet cast coating technique. However, in this method the cast-coated paper having a low surface strength is obtained and also, the production speed is still dissatisfied.

SUMMARY OF THE INVENTION

Accordingly, an object of the present invention is to provide a coating composition which makes it possible to improve the conventional method for manufacturing the cast-coated paper, in particular the rewet cast coating method whose production speed is relatively high and to provide the cast-coated paper having a high gloss and high surface strength and free of defects such as the formation of pits and further, having a good releasability from the cast drum and hence, preventing the formation of pits even during an extremely high speed production.

Another object of the present invention is to provide the cast-coated paper excellent in the releasability, gloss, surface strength and free of pits even when it is manufactured at a high speed which has never been achieved in the art.

Accordingly to one aspect of the present invention, there is provided a coating composition for the cast-coated paper which comprises mainly a pigment and an adhesive, characterized in that the adhesive comprises, per 100 parts by weight of the pigment, (A) 6 to 18 parts by weight, expressed in solid content, of a latex having an average particle size of 0.1 to 0.3 micron and (B) 3 to 12 parts by weight, expressed in solid content, of a latex or an acrylic emulsion having an average particle size of 0.5 to 1.5 micron the sum of the solid content of the components (A) and (B) being in the range of 9 to 30 parts by weight.

According to another aspect of the present invention, there is provided a coating composition for cast-coated paper which comprises mainly a pigment and an adhesive, characterized in that the adhesive comprises per 100 parts by weight of the pigment, (A) 2 to 15 parts by weight of casein; (B) 6 to 18 parts by weight, expressed in solid content, of a rubber latex having an average particle size ranging from 0.1 to 0.3 micron; (C) 3 to 12 parts by weight, expressed in solid content, of an acrylic emulsion or a secondary particle-forming rubber latex having an average particle size ranging from 0.1 to 0.3 micron; and (D) at least one inorganic compound selected from the group consisting of NaCl, Na_2SO_4 , ZnO and MgO and at least one organic salt selected from the group consisting of formates and acetates of calcium, zinc and magnesium the total solid content of the components (A), (B) and (C) being in the range of 18 to 40 parts by weight.

According to further another aspect of the present invention, there is provided a coating composition for making cast-coated paper which comprises mainly a pigment and an adhesive characterized in that the adhesive comprises a latex (A) having a gel content of not less than 50% and an acrylic emulsion (B) having a gel content of not less than 50%.

DETAILED DESCRIPTION OF THE INVENTION

In the present invention, the total amount (solid content per 100 parts by weight of the pigment used) of the binders (A) and (B) is limited to 9 to 30 parts by weight. This is because if the binders are used in a total amount of less than 9 parts by weight, the surface strength of the resulting cast-coated paper coated with such a paint is too low to be used in a practical printing operation, while if it is more than 30 parts by weight, the cast-coated paper coated with such a paint exhibits insufficient releasability which makes it difficult to achieve a high speed production of cast-coated paper. The preferred total amount ranges from 10 to 25 parts by weight.

Moreover, in the present invention, the amount of the latex (A) employed per 100 parts by weight of the pigment is restricted to 6 to 18 parts by weight (solid content). The reason of this is that if it is used in an amount less than 6 parts by weight, the resultant cast-coated paper has low surface strength while if the amount thereof exceeds 18 parts by weight, the releasability of the coated paper from the cast drum is dissatisfied, the coated paper has low permeability and a lot of pits are formed on the coated surface. The preferred amount of the latex (A) ranges from 7 to 16 parts by weight.

In addition, the amount of the binder (B) is limited to 3 to 12 parts by weight per 100 parts by weight of the pigment (solid content) in the present invention. This is because if it is less than 3 parts by weight, the adhesion between the cast drum and the coated surface of the paper is impaired, the gloss thereof is lowered and a lot of pits are formed on the resultant coated paper, while if it is more than 12 parts by weight, the releasability of the coated paper becomes insufficient and thus, pits are formed on the coated surface of the paper. The preferred amount is in the range of 4 to 10 parts by weight.

In the present invention, the average particle size of the latex (A) is restricted to 0.1 to 0.3 micron. This is because when the particle size is less than 0.1 micron, the resultant paint has high viscosity, the

releasability of the coated paper becomes insufficient and thus, it is difficult to obtain a smooth coated surface free of pits, even if the particle size of the binder (B) is limited to 0.5 to 1.5 micron. On the other hand, if the average particle size of the latex (A) exceeds 0.3 micron, the resulting cast-coated paper to which a paint containing such a latex is applied has a low surface strength and a lot of pits are formed thereon. Therefore, it is difficult to achieve the intended high speed production of cast-coated paper.

Moreover, the average particle size of the binder (B) is restricted to 0.5 to 1.5 micron. The reason of this is that if the average particle size of the binder (B) is less than 0.5 micron, the resulting cast-coated paper shows low permeability, many pits are formed thereon and thus, it is difficult to achieve the intended high speed production, while if it is more than 1.5 micron, the resultant cast-coated paper has a low surface strength and, therefore, printing operations cannot be carried out practically. In this respect, it should be noted that the binders (A) and (B) fulfill the requirement for the average particle size of the binders (A) and (B) after the preparation of the paint composition and that the average particle size of the binder by itself does not necessarily fall within the above defined range before the preparation of the composition. For instance, a latex (A) is prepared so as to have a chemically stable particle size ranging from 0.1 to 0.3 micron and separately a latex or acrylic emulsion having a particle size ranging from 0.1 to 0.3 followed by flocculating it through the addition of a small amount of polyvalent metal ions such as calcium or aluminum ions to control the particle size thereof to 0.5 to 1.5 micron, and then stabilizing it by adding a surfactant or a protective colloid agent to prepare the component (B). When a paint which has been obtained using the binders thus prepared is examined with a transmission electron microscope, it is confirmed, from the difference between the contrasts of the particle images, that the binders (A) and (B) independently maintain their particle size at the time of preparation, respectively. In other word, the latex (A) forms denser images in which the particles exist in the distinct state, while the acrylic emulsion (B) forms less dense images in which the particles exist as aggregates composed of several particles. This method for controlling particle size is described by way of example and it may be controlled during preparing the paint. The binder such as the aforementioned latex or acryl emulsion which is converted to the latex or acrylic emulsion (B) of the invention by adding a small amount of polyvalent metal cations or by aggregation operation during the process for preparing the paint will hereinafter be referred to as a precursor (B). It is also possible to use a binder (B) whose particle size is controlled so as to fall within the above defined range during synthesizing the same, but this is not economical.

The term "latex" herein used is the generic name of rubber type emulsions and, therefore, the components contained in the latex are polymers whose essential repeating units are those derived from diene monomers such as butadiene, isoprene and/or 2-chlorobutadiene. In addition, the term "acrylic emulsion" herein used is the generic name of polymer emulsions in which the polymer is principally composed of repeating units derived from the following monomers and does not contain diene type monomer units.

Examples of such monomers which may be used as copolymerizable monomer units other than diene type ones in the latex and which may be used as principal monomer units of the polymer in the acrylic emulsion are aromatic alkenyl compounds such as styrene, alpha-methyl styrene, chlorostyrene and dimethyl styrene; and mono-olefinic unsaturated compounds such as methyl acrylate, ethyl acrylate, butyl acrylate, 2-ethylhexyl acrylate, glycidyl acrylate, methyl methacrylate, ethyl methacrylate, butyl methacrylate, 2-ethylhexyl methacrylate, hydroxyethyl methacrylate, hydroxypropyl methacrylate, glycidyl methacrylate, acrylamide, N-methylol-acrylamide, N-methoxymethylacrylamide, methacrylamide, N-methylolmethacrylamide, N-methoxymethylmethacrylamide, acrylic acid, methacrylic acid, crotonic acid, alkyl fumarates, alkyl itaconates, acrylonitrile, methacrylonitrile, and vinyl acetate. These monomers may be used alone or in combination.

The binders used in the invention may be prepared by polymerizing or copolymerizing the foregoing monomers in the presence of a commonly used polymerization initiator such water-soluble peroxides as potassium persulfate, sodium persulfate and ammonium persulfate which may be used in combination with a water-soluble reducing agent such as sodium bisulfite, sodium sulfite and sodium thiosulfate. The polymerization reaction is generally carried out at a temperature of 50 to 100 °C and a gauge pressure of 0 to 10 kg/cm². All the monomers used in the polymerization may be added in one lot, in portions or continuously. In addition, it is also possible to add, during polymerization, such an emulsifying agent as sodium alkylbenzenesulfonates, sodium alkylsulfates and sodium alkylalcohol sulfates or such a protective colloid agent as a hydroxyethyl cellulose, carboxymethyl cellulose and polyvinyl alcohol. In this respect, the particle size of the resulting particles becomes small as the amount of the emulsifying agent with respect to the total amount of the monomers is increased and vice versa. Moreover, the molecular weight of the resultant particles may be controlled by the addition of a molecular weight controlling agent such a mercaptan as an alkylmercaptan and a tertiary mercaptan, carbon tetrachloride and a high alcohol. Thus,

the binder compositions having a particle size of 0.1 to 0.3 micron and 0.5 to 1.5 micron respectively used in the present invention can be freely prepared according to the foregoing constructions and methods.

The latex and acrylic emulsion as used herein preferably contain at least a certain level of toluene insolubles (generally referred to as "gel content") of the dried film thereof which relates to the molecular weight and the degree of cross-linking of the polymer included in the latex and acrylic emulsion. In order to ensure the intended high speed production, the gel content thereof is preferably not less than 15% by weight.

The pigments used in the present invention are not restricted to specific ones and examples thereof include such inorganic pigments as clay, calcium carbonate, titanium white, satin white, aluminum hydroxide, barium sulfate, zinc oxides and magnesium oxides; and organic pigments such as plastic pigments and white urea resin pigments.

The adhesive used herein may further comprise, in addition to the foregoing binders (A) and (B), water-soluble polymers such as casein and modified starch in an amount of 2 to 15 parts by weight per 100 parts by weight of the pigments present in the paint of this invention.

The paint composition of the present invention may contain, according to need, such a known coagulant as calcium formate, magnesium formate or zinc acetate; and/or such a known release agent as magnesium stearate or zinc stearate. The paint composition of the invention may contain anionic surfactants, nonionic surfactants or the like in addition to the previously added stabilizers for stably maintaining the aggregated state of particles of the binder (B).

Casein used as the component (A) in another aspect of the invention is preferably milk casein commonly used as a binder for pigment-coated paper. If the amount thereof is less than 2 parts by weight per 100 parts by weight of the pigment, the releasability of the cast-coated paper to which such a paint is applied becomes insufficient and thus the intended high speed production can be attained with substantial difficulty. While if it exceeds 15 parts by weight, the permeability of the coated layer is highly impaired and hence, a lot of pits are formed on the resultant cast-coated paper. The preferred amount of casein (A) ranges from 4 to 12 parts by weight.

Moreover, the rubber type latex as a component (B) of the adhesive is used in an amount of 6 to 18 parts by weight per 100 parts by weight of the pigment. This is because if it is less than 6 parts by weight, the resultant cast-coated paper shows low surface strength and cannot stand practical printing operations, on the other hand, if it is more than 18 parts by weight, the releasability of the coated paper becomes quite low, a lot of pits are formed thereon and, therefore, the intended high speed production is hard to achieve. The preferred amount of the rubber type latex (B) ranges from 7 to 16 parts by weight.

In addition, the acrylic emulsion or secondary particle-forming latex used as a component of the adhesive is used in an amount of 3 to 12 parts by weight per 100 parts by weight of the pigment. The reason of this is that if the amount of the component (C) is less than 3 parts by weight, the adhesion of the cast-coated paper to the drum surface is insufficient, gloss is lowered and a lot of pits are formed, while if the amount exceeds 12 parts by weight, the resulting cast-coated paper shows a low ink receptivity among the printability thereof and thus, a good printing surface cannot be obtained. The preferred amount of the component (C) ranges from 4 to 10 parts by weight.

The sum of the amount of these components (A) to (C) ranges from 18 to 40 parts by weight per 100 parts by weight of the pigment. This is because if it is less than 18 parts by weight, the resulting cast-coated paper has too low surface strength to stand practical printing operations, while it exceeds 40 parts by weight, properties of releasing the cast-coated paper from the drum surface become insufficient and hence, the high speed production thereof becomes very difficult. The preferred ranges from 20 to 35 parts by weight.

The term "rubber latex as a component (B)" herein used is the generic name of the rubber emulsions of copolymers having, as essential components (repeating units), those derived from butadiene and styrene or methyl methacrylate; and, as optional components, those derived from such non-ionic hydrophilic monomers as hydroxyethyl methacrylate, hydroxypropyl methacrylate, acrylamide, N-methylolacrylamide, N-methoxymethylacrylamide, methacrylamide, N-methylolmethacrylamide and N-methoxymethylmethacrylamide; and such anionic monomers as acrylic acid, itaconic acid and methacrylic acid, the total amount of these optional components being not less than 2% by weight, preferably not less than 2% by weight and less than 10% by weight. Diene type monomers such as isoprene and/or 2-chlorobutadiene may also be used instead of or in addition to butadiene. Examples of comonomer components used other than diene type monomers and styrene or methyl methacrylate are such aromatic alkenyl compounds as alpha-methylstyrene, chlorostyrene and such mono-olefin type unsaturated compounds as methyl acrylate, ethyl acrylate, butyl acrylate, 2-ethylhexyl acrylate, glycidyl acrylate, ethyl methacrylate, butyl methacrylate, 2-ethylhexyl methacrylate, glycidyl methacrylate, alkyl fumarates, alkyl itaconates, acrylonitrile,

methacrylonitrile and vinyl acetate. These monomers may be used alone or in combination.

The term "acrylic emulsion(s)" herein means those containing (co)polymers composed of repeating units derived from the monomer components listed above in connection with the rubber latex (B) except for diene type monomers, such as aromatic alkenyl compounds, acrylates, acrylamides, unsaturated carboxylic acids and their esters, nitriles and vinyl acetate. These monomers and copolymerizable monomers may be used alone or in combination.

The secondary particle-forming latex used as a component (C) is a latex of polymer composed of repeating units derived from the monomers listed above in connection with the rubber latex (B) provided that the sum of the non-ionic hydrophilic monomers and the anionic monomers is less than 2% by weight, preferably not less than 0.5% by weight and less than 2% by weight. The particle size of the secondary particles can freely be controlled by properly adjusting the total amount of these non-ionic hydrophilic monomers and the anionic monomers within the above defined range.

The particle size of the components (B) and (C) is generally in the range of 0.1 to 0.3 micron. In addition, these synthetic binders, preferably, comprise more than a certain level of toluene-solubles (commonly referred to as "gel content") of a dried film which relates to the molecular weight and the degree of cross-linking of the polymer. The gel content is preferably not less than 15% by weight in order to ensure the intended high speed production.

The adhesive may, further, include, as the component (D), both at least one inorganic substance selected from the group consisting of NaCl, Na₂SO₄, ZnO and MgO; and at least one organic acid salt selected from the group consisting of calcium, zinc and magnesium salts of formic acid or acetic acid. These additives are added to the paint composition in a small amount during preparation of the composition mainly composed of pigments, casein (A), the rubber latex (B) and the acrylic emulsion or secondary particle-forming latex (C) and selectively cause flocculation. The use of such a combination of at least one inorganic substance selected from the group consisting of NaCl, Na₂SO₄, ZnO and MgO; and at least one organic acid salt selected from the group consisting of calcium, zinc and magnesium salts of formic acid or acetic acid makes it possible to obtain a case-coated paper having good permeability and free of pits even when it is formed according to high speed production technique and case-coated surfaces which exhibit good gloss, high surface strength and excellent ink receptivity. Preferably, the inorganic and organic additives are composed of a combination of three components, i.e., one inorganic substances selected from the group consisting of NaCl and Na₂SO₄, one oxide selected from the group consisting of ZnO and MgO; and one organic acid salt selected from the group consisting of calcium, zinc and magnesium salts of formic acid or acetic acid.

The amount of these inorganic substances and the organic salts used is desirably determined so that the component (C) used as the synthetic binder having a particle size of 0.1 to 0.3 micron is selectively aggregated to from secondary particles and to increase the particle size of the resulting aggregates to 0.5 to 1.5 micron. In general, the amount ranges from 0.1 to 7 parts by weight for the inorganic substances and from 0.1 to 3 parts by weight for the organic salts, per 100 parts by weight of the pigment.

The manufacture of the components (B) and (C) can be carried out according to the aforementioned polymerization processes and conditions and the particle sizes of the resultant latex and the acrylic emulsion are adjusted to the ranges defined above according to the foregoing methods.

In addition, a protective colloid agent such as polyvinyl alcohol and hydroxyethyl cellulose, anionic surfactants, non-ionic surfactant or the like may be added to the paint composition, as a stabilizer, to stably maintain the aggregated state of the component (C) therein.

According to a further another aspect of the present invention, the adhesive contains both a latex (A) having a gel content of not less than 50% and an acrylic emulsion (B) having a gel content of not less than 50% to ensure the high speed production of cast-coated paper. In this connection, if the gel content of the latex (A) is less than 50%, the releasability of the coated paper from the drum surface becomes insufficient and it is difficult to obtain a smooth coated-surface having no pits, even if the gel content of the acrylic emulsion (B) simultaneously used is not less than 50%. Moreover, if that of the acrylic emulsion is less than 50%, the permeability of the cast-coated paper coated with such a paint composition is lowered, a lot of pits are formed and thus, the high speed production becomes difficult, even if the gel content of the latex (A) simultaneously used is not less than 50%. The latex (A) and the acrylic emulsion (B) are used in an amount of 5 to 19 parts by weight and 3 to 13 parts by weight per 100 parts by weight of the pigment, respectively.

The gel content of the latex can be adjusted through the use of such a mercaptan as an alkyl mercaptan or a tertiary mercaptan, or such a chain transfer agent as carbon tetrachloride and a high alcohol. It is effective to use these compounds not only independently but in combination of two or more of these. These compounds are used in an amount of not more than 5.0% by weight on the basis of the total

amount of the monomers. The gel content of the acrylic emulsions may be controlled according to a method of using such an auxiliary monomer component as a monomer having carboxyl group(s), a monomer having hydroxyl group(s), a monomer having methylol group(s) or a monomer having glycidyl group(s) to cause intra-or inter-molecular cross-linking reaction to thus adjust the gel content thereof; or a method in which a monomer having divinyl group(s) is used as an auxiliary monomer component. Either of these methods is effective to control the gel content and these methods may be employed in combination.

In this respect, examples of the monomers having carboxyl group(s) are acrylic acid, methacrylic acid, itaconic acid maleic acid, aconitic acid and citraconic acid; examples of monomers having hydroxyl group(s) are hydroxyethyl (meth)acrylate and hydroxypropyl (meth)acrylate; examples of monomers having methylol group(s) include methylol (meth)acrylamide and methoxymethyl (meth)acrylamide; and examples of monomers having glycidyl group(s) include glycidyl (meth)acrylate. These monomers having functional group(s) are preferably used in combination of at least two of these and in general these monomers having functional group(s) are used in an amount of 1.0 to 10% by weight on the basis of the total amount of the monomers. In addition, examples of monomers having divinyl group(s) include allyl (meth)acrylate, ethylene di(meth)acrylate, phenylene diacrylonitrile and divinylbenzene which may be used alone or in combination. The foregoing examples of the monomers having functional group(s) and the monomers having divinyl group(s) are simply exemplified by way of example and, therefore, monomers having reactive functional group(s) and those having polymerizable vinyl group(s) may likewise be used.

The cast-coated paper according to the present invention can be manufactured by applying a paint composition thus prepared to the surface of a base paper utilizing a known coating apparatus commonly used for manufacturing pigment-coated paper, such as an air knife coater, a roll coater or a blade coater, once drying the coated base paper, then rewetting with water and pressing the rewetted paper to a cast drum heated to a temperature of not less than 60°C at a linear pressure of not less than 10 kg/cm to dry the coated paper. The base paper is not restricted to a specific one in the present invention and may be any paper usually used for making pigment-coated paper.

The cast-coated paper thus prepared shows high surface strength and excellent gloss and has uniform surface free of pits as well as it has good ink receptivity, permeability and releasability. Thus, such a cast-coated paper can be produced according to the high speed production technique. The paint composition of the invention is useful as a paint for manufacturing the cast-coated paper according to not only the rewet cast coating technique but also the wet cast coating and gel cast coating techniques.

The present invention will hereunder be explained in more detail with reference to the following Examples and Comparative Examples, but the invention is never restricted to these Examples given below. In the following Examples and Comparative Examples, the terms "part(s)" and "%" are "part(s) by weight" and "% by weight" unless otherwise specified.

Example 1

In this example, methods for preparing a latex (A) herein used and a latex (B) herein used are first illustrated and then a method for preparing a paint composition according to the present invention is described.

(Preparation of Latex (A-1))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.2 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 part of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 15 hours after the initiation of the polymerization at which the degree of polymerization exceeded 98%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a latex (A-1). The particle size of the resultant latex was 0.15 micron.

(Preparation of Precursor of Latex (B))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.1 parts), potassium persulfate (0.8

parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 50 parts of styrene, 7 parts of methyl methacrylate and 3 parts of methacrylic acid (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 16 hours after the initiation of the polymerization at which the degree of polymerization exceeded 97%, cooling the reaction mixture, adjusting pH to 7 with aqueous ammonia solution to obtain the precursor of a latex (B). The particle size of the precursor of the latex (B) was 0.18 micron.

10 (Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein and 44.5 parts of water to dissolve these ingredients and 100 parts of water were charged into a Caurex mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components, adding 3.5 parts (corresponding to 0.7 parts expressed in the amount of solid content) of 20% aqueous solution of calcium acetate and then adding 12 parts (solid content) of the latex (A-1) and 7 parts (solid content) of the precursor of the latex (B) previously prepared. Finally, the solid content of the paint was controlled to 40% to obtain a paint composition-1 for cast-coated paper according to the present invention. The viscosity of the paint was 35 cps which was determined at 25°C and 60 r.p.m. using Brookfield Viscometer. In addition, the particle size of the latex in the paint was examined by a transmission electron microscope and found to be 0.15 μ m for the latex (A-1) and 0.85 to 0.95 μ m for the latex (B). The proportion of each ingredient of the paint composition-1, physical properties thereof and the like are listed in Table I given below.

Examples 2 to 7

Coating compositions 2 to 7 were prepared according to the same procedures and conditions as in Example 1 except that the amount of casein used; the amount of the latex (A-1) and the precursor of the latex (B) added and the total amount of these; as well as the amount of calcium acetate added were changed to those listed in Table I. The solid contents of these paint compositions, Brookfield viscosity, the particle size of the latexes (A-1) and (B) in the paint or the like were likewise determined or observed in the same manner as in Example 1 and the results thus obtained were also listed in Table I.

Example 8

In this Example, a method for preparing a latex (A-2) used herein and the preparation of a paint are illustrated.

(Preparation of Latex (A-2))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.3 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 14 hours after the initiation of the polymerization at which the degree of polymerization exceeded 98%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a latex (A-2). The particle size of the resultant latex was 0.1 micron.

55 (Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein, and 44.5 parts

of water to dissolve these ingredients and 100 parts of water were charged into a Cauress mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components, adding 1.5 parts (corresponding to 0.3 parts expressed in the amount of solid content) of 20% aqueous solution or calcium acetate and then adding 12 parts (solid content) of the latex (A-2) and 7 parts (solid content) of the precursor of the latex (B) previously prepared. Finally, the solid content of the paint was controlled at 40% to obtain a paint composition-8 for cast-coated paper according to the present invention. The viscosity of the paint was 120 cps which was determined at 25 °C and 60 r.p.m. using Brookfield Viscometer. In addition, the particle size of the resultant latex in the paint was examined by a transmission electron microscope and found to be 0.1 micron for the latex (A-2) and 0.5 to 0.7 micron for the latex (B). The proportion of each ingredient of the paint composition-8, physical properties thereof and the like are listed in Table I given below.

Example 9

A coating composition-9 was prepared according to the same procedures and conditions as in Example 8 except that the amount of calcium acetate in Example 1 was changed to that shown in Table I. The solid content of the paint composition, Brookfield viscosity, the particle size of the resultant latexes (A-2) and (B) in the paint or the like were likewise determined or observed in the same manner as in Example 8 and the resultant thus obtained were also listed in Table I.

Example 10

In this Example, a method for preparing a latex (A-3) herein used and the preparation of a paint are illustrated.

(Preparation of Latex (A-3))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.15 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70 °C, stopping the polymerization 16 hours after the initiation of the polymerization at which the degree of polymerization exceeded 98%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a latex (A-3). The size of the resultant latex particles was 0.3 micron.

(Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein, and 44.5 parts of water to dissolve these ingredients and 100 parts of water were charged into a Cauress mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components, adding 1.5 parts (corresponding to 0.3 parts expressed in the amount of solid content) of 20% aqueous solution of calcium acetate and then adding 12 parts (solid content) of the latex (A-3) and 7 parts (solid content) of the precursor of the latex (B) previously prepared. Finally, the solid content of the paint was controlled to 40% to obtain a paint composition-10 for cast-coated paper according to the present invention. The viscosity of the paint was 40 cps which was determined at 25 °C and 60 r.p.m. using Brookfield Viscometer. In addition, the size of the latex particles in the paint was examined by a transmission electron microscope and found to be 0.3 micron for the latex (A-3) and 0.5 to 0.7 micron for the latex (B). The proportion of each ingredient of the paint composition-10, physical properties thereof and the like are listed in Table I given below.

Example 11

A coating composition-11 was prepared according to the same procedures and conditions as in Example 10 except that the amount of calcium acetate in Example 10 was changed to that shown in Table I. The solid content of the paint composition, Brookfield viscosity, the particle size of the resultant latexes (A-3) and (B) in the paint or the like were likewise determined or observed in the same manner as in Example 10 and the results thus obtained were also listed in Table I.

Comparative Examples 1 to 6

Comparative compositions-1 to -6 were prepared according to the same procedures and conditions as in Example 1 except that the amount of casein used and the amount of calcium acetate used were changed as well as the amount of the latexes (A-1) and (B) and the total amount thereof were outside the range of the present invention, as listed in Table I. The solid content of these paints, Brookfield viscosity, and the particle size of the latexes (A-1) and (B) in the paint are also listed in Table I.

Comparative Examples 7 and 8

In this Comparative Example, the latexes (A-1) and (B) are independently used in paint compositions to make the effectiveness of the simultaneous use thereof more clear. In other words, Comparative compositions-7 and -8 were prepared according to the same procedures and conditions as in Example 1 except that the amount of calcium acetate was changed and that the latexes were separately used in the amount equal to the total amount of these two latexes in Example 1 (see Table I). The solid content of these paints, Brookfield viscosity, and the size of particles of the latexes in the paints are also listed in Table I.

Comparative Example 9

In this Comparative Example, a method for preparing a latex (A-4) used herein and the preparation of a paint are illustrated.

(Preparation of Latex (A-4))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.4 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 13 hours after the initiation of the polymerization at which the degree of polymerization exceeded 99%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a latex (A-4). The particle size of the resultant latex was 0.08 micron.

(Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein and 44.5 parts of water to dissolve these ingredients and 100 parts of water were charged into a Caurex mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components and then adding 12 parts (solid content) of the latex (A-4) and 7 parts (solid content) of the precursor of the latex (B) previously prepared. Finally, the solid content of the paint was controlled to 40% to obtain a comparative paint composition-9 for cast-coated paper. The viscosity of the paint was 825 cps which was determined at 25°C and 60 r.p.m. using Brookfield Viscometer. In addition, the size of the latex particles in the paint was examined by a transmission electron microscope and found to be 0.08 micron for the latex (A-4) and 0.18

micron for the latex (B). The proportion of each ingredient of the comparative paint composition-9, physical properties thereof and the like are listed in Table I given below.

5 Comparativ Example 10

In this Comparative Example, a method for preparing a latex (A-5) herein used and the preparation of a paint are illustrated.

10

(Preparation of Latex (A-5))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.1 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of
 15 styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 18 hours after the initiation of the polymerization at which the degree of polymerization exceeded 97%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a latex (A-
 20 5). The size of the resultant latex particles was 0.35 micron.

(Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein and 44.5 parts of water to dissolve these ingredients and 100 parts of water were charged into a Cauress mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60
 30 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components, adding 7 parts (corresponding to 1.4 parts expressed in solid content) of 20% aqueous solution of calcium acetate and then adding 12 parts (solid content) of the latex (A-5) and 7 parts (solid content) of the precursor of the latex (B) previously prepared. Finally, the solid content of the paint was controlled to 40% to obtain a comparative paint composition-10 for cast-coated paper. The viscosity of the paint was 26 cps which was determined at 25°C and 60 r.p.m. using Brookfield Viscometer. In addition, the size of the latex particles in
 35 the paint was examined by a transmission electron microscope and found to be 0.35 micron for the latex (A-5) and 1.08 to 2.16 micron for the latex (B). The proportion of each ingredient of the comparative paint composition-10, physical properties thereof and the like are listed in Table I given below.

40 Test Example

Each of the coating compositions obtained in the foregoing Examples and Comparative Examples was applied to the surface of base paper having a basis weight of 64.0 g/m² with an air-knife coater in an amount of 25 g/m² (weighed after drying), was dried, was supplied with a rewetting solution and then
 45 passed through a cast drum. The casting was carried out utilizing a drum having a diameter of 1200 mm, at a linear pressure of 50 kg/cm and a surface temperature of 95 to 100°C to obtain maximum casting speed at which good releasability is maintained and no pits are formed on the paper surface. In addition, the permeability of the coated paper prior to casting was determined and the gloss and surface strength of the resultant cast-coated paper were estimated. The results thus obtained are listed in Table II given below. In
 50 this respect, the permeability was determined with a permeability tester (developed by OKEN) and the gloss was determined in accordance with JIS P-8142. The surface strength was determined by RI Printing Tester (available from MEI MANUFACTURING CO., LTD.) and visually observing the surface to estimate it according to 10-stage evaluation. 10th stage stands for the best surface having no picking, 1st stage the worst surface having picking throughout the surface and thus the estimation

55

Table I

Ingredients of Coating Composition	Example										Comparative Example										
	1	2	3	4	5	6	7	8	9	10	11	1	2	3	4	5	6	7	8	9	10
Kaolin	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60
Calcium carbonate	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40
Casein	8	11	5	12	4	13	5	8	8	8	8	14	1	9	10	4	14	8	8	8	8
Calcium acetate	0.7	0.4	1.0	0.7	0.8	0.4	1.0	0.3	1.0	0.3	1.0	0.1	0.7	1.3	0.7	1.4	0.2	-	1.9	-	1.4
Latex (A)	A-1 12	A-1 12	A-1 12	A-1 7	A-1 16	A-1 6	A-1 15	A-2 12	A-2 12	A-3 12	A-3 12	A-1 12	A-1 19	A-1 12	A-1 4	A-1 19	A-1 4	A-1 19	A-4 12	A-5 12	A-5 12
Latex (B)	7	4	10	7	8	4	10	7	7	7	7	1	7	13	7	14	2	-	19	7	7
(A) + (B)	19	16	22	14	24	10	25	19	19	19	19	13	26	25	11	33	6	19	19	19	19
Physical Properties of Coating Composition																					
Solid content (%)	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40
Viscosity (cps)	35	70	30	85	30	105	25	120	100	40	30	235	23	40	65	35	580	85	30	825	26
Particle size of latex in the coating composition (μm)																					
(A)	0.15	0.15	0.15	0.15	0.15	0.15	0.15	0.1	0.1	0.3	0.3	0.15	0.15	0.15	0.15	0.15	0.15	0.15	-	0.08	0.15
(B)	0.85	0.85	0.85	0.85	0.85	0.85	0.85	0.5	1.1	0.5	1.1	0.85	0.85	0.85	0.85	0.85	0.85	0.85	-	0.85	1.08
	0.95	0.95	0.95	0.95	0.95	0.95	0.95	0.7	1.5	0.7	1.5	0.95	0.95	0.95	0.95	0.95	0.95	0.95	-	0.95	2.16

Table II

Coating Composition	Casting Speed (m/min.)	Permeability Prior to Casting	Cast-coated Paper		Coating Composition	Casting Speed (m/min.)	Permeability Prior to Casting	Cast-coated Paper	
			Surface Strength	Gloss				Surface Strength	Gloss
Example 1	65	1600	10	90	Comp. Ex. 1	45	2350	10	85
Example 2	60	1850	10	89	Comp. Ex. 2	35	2300	9	92
Example 3	65	1400	9	90	Comp. Ex. 3	30	3900	10	90
Example 4	65	1500	10	89	Comp. Ex. 4	45	1000	5	80
Example 5	60	1720	10	91	Comp. Ex. 5	25	7400	10	89
Example 6	65	1330	9.5	88	Comp. Ex. 6	45	1200	6	85
Example 7	65	1480	10	91	Comp. Ex. 7	30	5500	10	82
Example 8	60	1950	10	91	Comp. Ex. 8	45	1500	5	92
Example 9	60	1700	9.5	90	Comp. Ex. 9	25	7800	10	88
Example 10	65	1280	9.5	89	Comp. Ex. 10	30	1200	3	80
Example 11	65	1150	9	88					

was performed according to 10 stages of evaluation from 1st stage to 10th stage.

Example 12

(Preparation of Latex (A-6))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.2 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 15 hours after the initiation of the polymerization at which the degree of polymerization exceeded 98%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a latex (A-6). The size of the resultant latex particles was 0.15 micron.

(Preparation of Precursor of Acrylic Emulsion (B))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.1 parts), ammonium persulfate (0.8 parts), and monomer components, i.e., 40 part of butyl acrylate, 50 parts of styrene, 7 parts of methyl methacrylate and 3 parts of methacrylic acid (100 parts of monomers in all) were charged into a three-necked glass reactor purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 8 hours after the initiation of the polymerization at which the degree of polymerization exceeded 97%, cooling the reaction mixture, adjusting pH to 7 with an aqueous ammonia solution to obtain a precursor of acryl emulsion (B). The particle size of the resultant precursor was 0.18 micron.

(Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein and 44.5 parts of water to dissolve these ingredients and 100 parts of water were charged into a Cauress mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components, adding 3.5 parts (corresponding to 0.7 parts expressed in solid content) of 20% aqueous solution of calcium acetate and then adding 12 parts (solid content) of the latex (A-6) and 7 parts (solid content) of the precursor of the latex (B) prepared above. Finally, the solid content of the paint was controlled to 40% to obtain a paint composition-12 for cast-coated paper according to the present invention. The viscosity of the paint was 30 cps which was determined at 25°C and 60 r.p.m. using Brookfield Viscometer. In addition, the size of the synthetic binders in the paint was examined by a transmission electron microscope and found to be 0.15 micron for the latex (A-6) and 0.85 to 1.0 micron for the acryl emulsion (B). The proportion of each ingredient of the paint composition 12, physical properties thereof and the like are listed in Table III given below.

Examples 13 to 18

Paint compositions 13 to 18 were prepared according to the same procedures and conditions as in Example 12 except that the amount of casein used; the amount of the latex (A-6) and the precursor of the latex (B) added and the total amount of these; as well as the amount of calcium acetate added were changed to those listed in Table III. The solid contents of these paint compositions, Brookfield viscosity, the particle size of the latex (A-6) and the acryl emulsion (B) in the paint or the like were likewise determined or observed in the same manner as in Example 12 and the results thus obtained were also listed in Table III.

Example 19

(Preparation of Latex (A-7))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.3 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70° C, stopping the polymerization 14 hours after the initiation of the polymerization at which the degree of polymerization exceeded 98%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a latex (A-7). The size of the resultant latex particles was 0.1 micron.

(Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein and 44.5 parts of water to dissolve these ingredients and 100 parts of water were charged into a Caurex mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components, adding 1.5 parts (corresponding to 0.3 parts expressed in the amount of solid content) of 20% aqueous solution of calcium acetate and then adding 12 parts (solid content) of the latex (A-7) and 7 parts (solid content) of the precursor of the acryl emulsion (B) previously prepared. Finally, the solid content of the paint was controlled to 40% to obtain a paint composition-19 for cast-coated paper according to the present invention. The viscosity of the paint was 115 cps which was determined at 25° C and 60 r.p.m. using Brookfield Viscometer. In addition, the size of the latex particles in the paint was examined by a transmission electron microscope and found to be 0.1 micron for the latex (A-7) and 0.5 to 0.7 micron for the acryl emulsion (B). The proportion of each ingredient of the paint composition-19, physical properties thereof and the like are listed in Table III given below.

30

Example 20

A paint composition-20 was prepared according to the same procedures and conditions as in Example 19 except that the amount of calcium acetate in Example 19 was changed to that shown in Table III. The solid content of the paint composition, Brookfield viscosity, the particle size of the latex (A-7) and the acryl emulsion (B) in the paint or the like were likewise determined or observed in the same manner as in Example 19 and the results thus obtained were also listed in Table III.

40 Example 21

(Preparation of Latex (A-8))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.15 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70° C, stopping the polymerization 16 hours after the initiation of the polymerization at which the degree of polymerization exceeded 98%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a latex (A-8). The size of the latex particles was 0.3 micron.

55 (Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein and 44.5 parts.

of water to dissolve these ingredients and 100 parts of water were charged into a Cauress mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components, adding 1.5 parts (corresponding to 0.3 parts expressed in the amount of solid content) of 20% aqueous solution of calcium acetate and then adding 12 parts (solid content) of the latex (A-8) and 7 parts (solid content) of the precursor of the acryl emulsion (B) previously prepared. Finally, the solid content of the paint was controlled to 40% to obtain a paint composition-21 for cast-coated paper according to the present invention. The viscosity of the paint was 35 cps which was determined at 25° C and 60 r.p.m. using Brookfield Viscometer. In addition, the size of the latex particles in the paint was examined by a transmission electron microscope and found to be 0.3 micron for the latex (A-8) and 0.5 to 0.7 micron for the acryl emulsion (B). The proportion of each ingredient of the paint composition-21, physical properties thereof and the like are listed in Table III given below.

Example 22

A paint composition-22 was prepared according to the same procedures and conditions as in Example 21 except that the amount of calcium acetate in Example 21 was changed to that shown in Table III. The solid content of the paint composition, Brookfield viscosity, the particle size of the latex (A-8) and the acryl emulsion (B) in the paint or the like were likewise determined or observed in the same manner as in Example 21 and the results thus obtained were also listed in Table III.

Comparative Examples 11 to 16

Comparative compositions-11 to -16 were prepared according to the same procedures and conditions as in Example 12 except that the amount of casein used and the amount of calcium acetate used were changed as well as the amount of the latex (A-6) and the precursor of the acryl emulsion (B) and the total amount of these were outside the range of the present invention. The solid content of these paints, Brookfield viscosity, and the particle size of the latex (A-6) and the acryl emulsion (B) in the paints are also listed in Table III.

Comparative Examples 17 and 18

In this Comparative Example, the latex (A-6) and the acryl emulsion (B) are independently used in paint compositions to make the effectiveness of the simultaneous use thereof more clear. In other words, Comparative compositions-17 and -18 were prepared according to the same procedures and conditions as in Example 12 except that the amount of calcium acetate was changed and that the latex and the acryl emulsion were separately used in the amount equal to the total amount of these two binders in Example 12 (see Table III). The solid content of these paints, Brookfield viscosity, and the particle size of the latex and the acryl emulsion in the paints are also listed in Table III.

Comparative Example 19

(Preparation of Latex (A-9))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.4 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70° C, stopping the polymerization 13 hours after the initiation of the polymerization at which the degree of polymerization exceeded 99%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a latex (A-9). The size of the resultant latex was 0.08 micron.

(Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein and 44.5 parts of water to dissolve these ingredients and 100 parts of water were charged into a Caurex mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components and then adding 12 parts of the latex (A-9) and 7 parts (solid content) of the precursor of the acryl emulsion (B) previously prepared. Finally, the solid content of the paint was controlled to 40% to obtain a comparative paint composition-19 for cast-coated paper. The viscosity of the paint was 460 cps which was determined at 25°C and 60 r.p.m. using Brookfield Viscometer. In addition, the size of the latex particles in the paint was examined by a transmission electron microscope and found to be 0.08 micron for the latex (A-9) and 0.18 micron for the acryl emulsion (B). The proportion of each ingredient of the comparative paint composition-19, physical properties thereof and the like are listed in Table III given below.

Comparative Example 20

(Preparation of Latex (A-10))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.1 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 18 hours after the initiation of the polymerization at which the degree of polymerization exceeded 97%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a latex (A-10). The size of the resultant latex particles was 0.35 micron.

(Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein and 44.5 parts of water to dissolve these ingredients and 100 parts of water were charged into a Caurex mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components, adding 7 parts (corresponding to 1.4 parts expressed in solid content) of 20% aqueous solution of calcium acetate and then adding 12 parts (solid content) of the latex (A-10) and 7 parts (solid content) of the precursor of the acryl emulsion (B) previously prepared. Finally, the solid content of the paint was controlled to 40% to obtain a comparative paint composition-20 for cast-coated paper. The viscosity of the paint was 25 cps which was determined at 25°C and 60 r.p.m. using Brookfield Viscometer. In addition, the size of the latex particles in the paint was examined by a transmission electron microscope and found to be 0.35 micron for the latex (A-10) and 1.08 to 2.16 micron for the acryl emulsion (B). The proportion of each ingredient of the comparative paint composition-20, physical properties thereof and the like are listed in Table III given below.

Test Example

According to the same manner as in the foregoing Test Example, a cast-coated paper was prepared using the paint compositions prepared in the foregoing Examples and Comparative Examples and the casting speed, permeability, glossiness and surface strength were determined. The results thus obtained are summarized in the following Table IV.

As seen from the data listed in Tables II and IV, according to the paint compositions of the invention in which each component fulfills the corresponding requirements, there are provided cast-coated papers having well-balanced qualities such as gloss, surface strength and permeability regardless of the paper

being prepared by high speed production. This clearly indicates that the paint compositions according to the present invention are very useful ones for preparing the cast-coated paper, quite unlike the conventional ones.

5

Examples 23

(Preparation of Rubber type Latex (B))

10

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.2 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional

15

20

25

30

35

40

45

50

55

Table III

	Example												Comparative Example											
Ingredients of Coating Composition	12	13	14	15	16	17	18	19	20	21	22		11	12	13	14	15	16	17	18	19	20		
	60	60	60	60	60	60	60	60	60	60	60		60	60	60	60	60	60	60	60	60	60		
Caolin	40	40	40	40	40	40	40	40	40	40	40		40	40	40	40	40	40	40	40	40	40		
Calcium carbonate	8	11	5	12	4	13	5	8	8	8	8		14	1	9	10	4	15	8	8	8	8		
Casein	0.7	0.4	1.0	0.7	0.8	0.4	1.0	0.3	1.0	0.3	1.0		0.7	0.7	1.3	0.1	1.2	0.2	1.9	-	-	1.4		
Calcium acetate	A-6 12	A-6 12	A-6 12	A-6 7	A-6 16	A-6 6	A-6 15	A-7 12	A-7 12	A-8 12	A-8 12		A-6 12	A-6 19	A-6 12	A-6 4	A-6 19	A-6 4	A-6 -	A-6 19	A-9 12	A-10 12		
Latex (A)	7	4	10	7	8	4	10	7	7	7	7		1	7	13	7	14	2	19	-	7	7		
Acrylic emulsion (B)	19	16	22	14	24	10	25	19	19	19	19		13	26	25	11	33	6	19	19	19	19		
(A) + (B)																								
Physical Properties of Coating Composition																								
Solid content (%)	40	40	40	40	40	40	40	40	40	40	40		40	40	40	40	40	40	40	40	40	40		
Viscosity (cps)	30	55	28	80	25	95	30	115	100	35	20		210	20	37	55	30	190	35	95	460	25		
Particle size of Synthetic Binders in Coating Composition (µm)																								
(A)	0.15	0.15	0.15	0.15	0.15	0.15	0.15	0.1	0.1	0.3	0.3		0.15	0.15	0.15	0.15	0.15	0.15	-	0.15	0.08	0.35		
(B)	0.85 2	0.85 2	0.85 2	0.85 2	0.85 2	0.85 2	0.85 2	0.5 2	1.1 2	0.5 2	1.1 2		0.85 2	0.85 2	0.85 2	0.85 2	0.85 2	0.85 2	-	-	0.18 2	1.08 2		
	1.0	1.0	1.0	1.0	1.0	1.0	1.0	0.7	1.5	0.7	1.5		1.0	1.0	1.0	1.0	1.0	1.0	1.0	-	-	2.16		

Table IV

Coating Composition	Casting Speed (m/min.)	Permeability Prior to Casting	Cast-coated Paper		Coating Composition	Casting Speed (m/min.)	Permeability Prior to Casting	Cast-coated Paper	
			Surface Strength	Gloss				Surface Strength	Gloss
Example 12	65	1350	10	91	Comp. Ex. 11	45	2100	10	79
Example 13	65	1500	10	91	Comp. Ex. 12	35	2000	7	92
Example 14	70	1150	9	92	Comp. Ex. 13	40	3450	10	90
Example 15	70	1200	9.5	90	Comp. Ex. 14	45	900	6	81
Example 16	65	1400	10	91	Comp. Ex. 15	35	4550	10	88
Example 17	70	1100	9	90	Comp. Ex. 16	45	1150	5	73
Example 18	65	1210	10	91	Comp. Ex. 17	45	1000	4	92
Example 19	65	1850	10	92	Comp. Ex. 18	35	5000	10	84
Example 20	65	1600	9.5	91	Comp. Ex. 19	30	6500	10	87
Example 21	70	1250	9.5	91	Comp. Ex. 20	35	950	3	72
Example 22	70	1000	9	90					

monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 15 hours after the initiation of the polymerization at which the degree of polymerization exceeded 98%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a rubber type latex (B). The particle size of the resultant latex was found to be 0.15 micron.

(Preparation of Acrylic Emulsion (C))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.1 parts), ammonium persulfate (0.8 parts), and monomer components, i.e., 40 parts of butyl acrylate, 50 parts of styrene, 7 parts of methyl methacrylate and 3 parts of methacrylic acid (100 parts of monomers in all) were charged into a three-necked glass reactor purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 8 hours after the initiation of the polymerization at which the degree of polymerization exceeded 97%, cooling the reaction mixture, adjusting pH to 7 with an aqueous ammonia solution to obtain an acryl emulsion (C). The particle size of the resultant acryl emulsion was 0.18 micron.

(Preparation of Coating Composition)

60 Parts of an aqueous casein solution (corresponding to 9 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.9 parts), 9 parts of milk casein and 50.1 parts of water to dissolve these ingredients and 100 parts of water were charged into a Caress mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components and then adding 12 parts (solid content) of the rubber type latex (B) and 7 parts (solid content) of the acryl emulsion (C) previously prepared. Then, 0.3 parts of sodium chloride, 3 parts of zinc oxide and 0.7 parts of calcium acetate (solid content each) were added to the mixture, finally pH thereof was adjusted to 7 with ammonia and the solid content of the paint was controlled to 40% to obtain a paint composition-23 for cast-coated paper according to the present invention. The viscosity of the paint was 38 cps which was determined at 25°C and 60 r.p.m. using Brookfield Viscometer. The proportion of each ingredient of the paint composition-23, physical properties thereof and the like are listed in Table V given below.

Examples 24 to 32

Paint compositions 24 to 32 were prepared according to the same procedures and conditions as in Example 23 except for changing the amount of casein used, the amount of the rubber type latex (B) and the acryl emulsion (C), the total amount of these binders and the amount of sodium chloride, zinc oxide and calcium acetate to those listed in Table V. The solid contents and Brookfield Viscosities of these paint compositions were determined in the same manner as in Example 23 and the results obtained were summarized in Table V.

Comparative Examples 21 to 29

Paint compositions 21 to 28 were prepared according to the same procedures and conditions as in Example 23 except for changing the amount of chloride, zinc oxide and calcium acetate, the amount of casein used and the amount of the rubber type latex (B) and the acryl emulsion (C), and the total amount of these two binders to those listed in Table V. A paint composition 29 was prepared according to the same procedures and conditions as in Example 23 except that inorganic additives were not used and that calcium acetate was used. The solid contents and Brookfield viscosities of these paint compositions are also summarized in Table V.

Comparative Examples 30 and 31

In these Comparative Examples, there are illustrated experiments in which the rubber type latex (B) and the acryl emulsion (C) are separately employed in the paint compositions in order to make the effectiveness of the simultaneous use of these two synthetic binders more clear. In other words, Comparative compositions 30 and 31 were prepared according to the same procedures and conditions as in Example 23 except that the amount of calcium acetate was changed and that the rubber type latex (B) and the acryl emulsion (C) were separately used in the amount equal to the total amount of these two binders in Example 23. The solid content of these paints and Brookfield viscosity thereof are also listed in Table V.

10 Test Example

Each of the paint compositions obtained in the foregoing Examples and Comparative Examples was applied to the surface of base paper having a basis weight of 64.0 g/m² with an air-knife coater in an amount of 25 g/m² (weighed after drying), was dried, was supplied with a rewetting solution and then passed through a casting drum. The casting was carried out utilizing a drum having a diameter of 1200 mm, at a linear pressure of 50 kg/cm and a surface temperature of 95 to 100 °C to obtain maximum casting speed at which good releasability are maintained and no pits are formed on the paper surface. In addition, the permeability of the coated paper prior to casting was determined and the gloss and surface strength of the resultant cast-coated paper were estimated. The results thus obtained are listed in Table VI given below. In this respect, the permeability was determined with a permeability Tester (developed by OKEN) and the gloss was determined in accordance with JIS-P-8142. The ink receptibility was determined by RI Printing Tester (available from MEI MANUFACTURING CO.) and measuring ink receptive density on the printed surface with Macbeth type ink densitometer (available from TOKYO DENSHOKU CO., LTD.). The results obtained are listed in Table VI.

25

Example 33

30 (Preparation of Rubber type Latex (B))

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.2 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70 °C, stopping the polymerization 15 hours after the initiation of the polymerization at which the degree of polymerization exceeded 98%, cooling the reaction mixture, adjusting pH to 7 with sodium hydroxide to obtain a rubber type latex (B). The particle size of the latex was found to be 0.15 micron.

40

(Preparation of Secondary Particle-Forming Latex (C))

Deionized water (120 parts), sodium

45

50

55

Table V

	Example										Comparative Example										
Ingredients of Coating Composition	23	24	25	26	27	28	29	30	31	32	21	22	23	24	25	26	27	28	29	30	31
	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60	60
Kaolin	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40
Calcium carbonate	9	9	9	9	9	4	12	5	10	9	9	9	9	9	1	17	4	14	9	9	9
Casein (A)	12	12	12	16	7	12	12	10	10	12	12	12	19	5	12	12	8	17	12	19	-
Latex (B)	7	4	10	7	7	7	7	5	10	7	2	14	7	7	7	7	4	11	7	-	19
Acrylic emulsion (C)	28	25	31	32	23	23	31	20	35	28	23	35	35	21	20	36	16	42	28	28	28
Total amount of Binders	0.3	0.3	0.3	0.3	0.3	0.1	0.4	0.2	0.3	-	0.3	0.3	0.3	0.3	0.1	0.6	0.1	0.5	-	0.3	0.3
Sodium chloride	3	3	3	3	3	1.3	4	1.7	3.3	3	3	3	3	3	0.3	5.7	1.3	4.7	-	3	3
Zinc oxide	0.7	0.4	1.0	0.7	0.7	0.7	0.7	0.5	1.0	0.7	0.2	1.4	0.7	0.7	0.7	0.7	0.4	1.1	0.7	-	0.7
Calcium acetate	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40	40
Solid content of Coating Composition (Z)	38	45	30	40	55	25	85	28	60	30	45	25	48	60	18	1840	23	360	20	275	25
Viscosity of Coating Composition (cps)																					

Table VI

Coating Composition	Casting Speed (m/min.)	Permeability Prior to Casting	Cast-coated Paper		Ink Receptivity	Coating Composition	Casting Speed (m/min.)	Permeability Prior to Casting	Cast-coated Paper		Ink Receptivity
			Surface Strength	Gloss					Surface Strength	Gloss	
Example 23	75	450	10	92	1.75	Comp. Ex. 21	55	440	9.5	76	1.77
Example 24	75	430	10	92	1.76	Comp. Ex. 22	50	860	10	92	1.62
Example 25	75	480	10	93	1.73	Comp. Ex. 23	45	1100	10	91	1.76
Example 26	75	680	10	93	1.76	Comp. Ex. 24	45	350	7	89	1.75
Example 27	75	400	9	92	1.75	Comp. Ex. 25	45	300	3	87	1.78
Example 28	75	380	9	93	1.74	Comp. Ex. 26	40	2150	10	91	1.73
Example 29	75	600	10	91	1.76	Comp. Ex. 27	55	320	5	86	1.76
Example 30	75	350	9	89	1.75	Comp. Ex. 28	45	3100	10	91	1.64
Example 31	70	730	10	92	1.73	Comp. Ex. 29	40	3400	10	90	1.74
Example 32	70	500	10	91	1.76	Comp. Ex. 30	35	5150	10	80	1.79
						Comp. Ex. 31	50	250	6	93	1.60

dodecylbenzenesulfonate (0.1 parts), ammonium persulfate (0.8 parts), t-dodecyl mercaptan (0.4 parts), and monomer components, i.e., 25 part of butadiene, 64 parts of styrene, 7 parts of methyl methacrylate, 3 parts of methacrylic acid and 1 part of methylolmethacrylamide (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70°C, stopping the polymerization 13 hours after the initiation of the polymerization at which the degree of polymerization exceeded 98%, cooling the reaction mixture, adjusting pH to 7 with an aqueous ammonia solution to obtain a secondary particle-forming latex (C). The particle size of the resultant latex was 0.19 micron.

(Preparation of Coating Composition)

60 Parts of an aqueous casein solution (corresponding to 9 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.9 parts), 9 parts of milk casein and 50.1 parts of water to dissolve these ingredients and 100 parts of water were charged into a Caurex mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components and then adding 12 parts (solid content) of the rubber type latex (B) and 7 parts (solid content) of the secondary particle-forming latex (C) previously prepared. Then, 0.3 parts of sodium chloride, 3 parts of zinc oxide and 0.7 parts of calcium acetate (solid content each) were added to the mixture, finally pH thereof was adjusted to 8.0 with ammonia and the solid content of the paint was controlled to 40% to obtain a paint composition-33 for cast-coated paper according to the present invention. The viscosity of the paint was 45 cps which was determined at 25°C and 60 r.p.m. using Brookfield Viscometer. The proportion of each ingredient of the paint composition-33, physical properties thereof and the like are listed in Table VII given below.

Example 34 to 42

Coating compositions 34 to 42 were prepared according to the same procedures and conditions as in Example 33 except for changing the amount of casein used, the amount of the rubber type latex (B) and the secondary particle-forming latex (C), the total amount of these binders and the amount of sodium chloride, zinc oxide and calcium acetate to those listed in Table VII. The solid contents and Brookfield viscosities of these paint compositions were determined in the same manner as in Example 33 and the results obtained were summarized in Table VII.

Comparative Examples 32 to 40

Comparative paint compositions 32 to 39 were prepared according to the same procedures and conditions as in Example 33 except that the amounts of sodium chloride, zinc oxide and calcium acetate were changed as listed in Table VII and that the amount of casein used and the amount of the rubber type latex (B) and the secondary particle-forming latex (C) as well as the total amount of these binders used were outside the range of this invention as shown in Table VII. A comparative paint composition 40 was prepared according to the same procedures and conditions as in Example 33 except that inorganic additives were not used and that calcium acetate was used instead. The solid contents and Brookfield viscosities of these comparative paint compositions are also summarized in Table VII.

Comparative Examples 41 and 42

In these Comparative Examples, there are illustrated experiments in which the rubber type latex (B) and the secondary particle-forming latex (C) are separately employed in the paint compositions in order to make the effectiveness of the simultaneous use of these two synthetic binders more clear. In other words, comparative compositions 41 and 42 were prepared according to the same procedures and conditions as in Example 33 except that the amount of calcium acetate was changed as shown in Table VII and that the latexes (B) and (C) were separately used in the amount equal to the total amount of these two binders in Example 33. The solid content of these paints and Brookfield viscosity thereof are also listed in Table VII.

Test Example

Cast-coated paper was prepared using the paint compositions obtained in the foregoing Examples and Comparative Examples in the same manner as in the aforementioned Test Example and casting speed, permeability, glossiness, surface strength and ink receptivity were likewise determined. The results thus obtained are summarized in Table VIII given below.

As seen from the data listed in Tables VI and VIII, according to the paint compositions of the present invention in which each component fulfills the corresponding requirements, there are provided cast-coated papers having well-balanced qualities such as gloss, surface strength and permeability regardless of the paper being prepared by high speed production technique. This clearly indicates that the paint compositions according to the present invention are very useful ones for preparing the cast-coated paper, quite unlike the conventional ones.

Example 43

(Preparation of Latex (A) 1)

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.2 parts), potassium persulfate (0.8 parts), t-dodecyl mercaptan (hereunder referred to as "TDM"; 0.6 parts), and monomer components, i.e., 40 parts of butadiene, 45 parts of styrene, 8 parts

Table VII

	Example												Comparative Example											
	33	34	35	36	37	38	39	40	41	42			32	33	34	35	36	37	38	39	40	41	42	
Ingredients of Coating Composition																								
Kaolin	60	60	60	60	60	60	60	60	60	60	60		60	60	60	60	60	60	60	60	60	60	60	
Calcium carbonate	40	40	40	40	40	40	40	40	40	40	40		40	40	40	40	40	40	40	40	40	40	40	
Casein (A)	9	9	9	9	9	9	4	12	5	10	9		9	9	9	9	1	17	4	14	9	9	9	
Latex (U)	12	12	12	16	7	12	12	12	10	15	12		12	12	19	5	12	12	8	17	12	19	-	
Latex (C)	7	4	10	7	7	7	7	7	5	10	7		2	14	7	7	7	7	4	11	7	-	19	
Total amount of Binders	28	25	31	32	23	23	23	31	20	35	28		23	35	35	21	20	36	16	42	28	28	28	
Sodium chloride	0.3	0.3	0.3	0.3	0.3	0.3	0.1	0.4	0.2	0.3	-		0.3	0.3	0.3	0.3	0.1	0.6	0.1	0.5	-	0.3	0.3	
Zinc oxide	3	3	3	3	3	3	1	4	2	3	3		3	3	3	3	1	6	1	5	-	3	3	
Calcium acetate	0.7	0.4	1.0	0.7	0.7	0.7	0.7	0.7	0.5	1.0	0.7		0.2	1.4	0.7	0.7	0.7	0.7	0.8	1.7	0.7	-	1.9	
Solid content of Coating Composition (Z)	40	40	40	40	40	40	40	40	40	40	40		40	40	40	40	40	40	40	40	40	40	40	
Viscosity of Coating Composition (cps)	45	52	35	40	50	30	92	35	70	37			50	34	55	65	28	1750	33	400	45	310	35	
Particle size of Latex in Coating Composition (µm)																								
(B)	0.15	0.15	0.15	0.1	0.15	0.3	0.1	0.3	0.15	0.15			0.15	0.15	0.15	0.15	0.15	0.15	0.35	0.08	0.15	0.15	-	
(C)	0.75	0.75	0.75	0.75	0.75	0.9	0.5	0.9	0.75	1.05			0.75	0.75	0.75	0.75	1.2	0.3	1.35	0.3	1.35	-	0.75	
	1.05	1.05	1.05	1.05	1.05	1.2	0.9	1.5	1.05	1.5			1.05	1.05	1.05	1.05	1.5	0.45	2.1	0.6	1.8	1.05		

Table VIII

Coating Composition	Casting Speed (m/min.)	Permeability Prior to Casting	Cast-coated Paper		Ink Receptivity	Coating Composition	Casting Speed (m/min.)	Permeability Prior to Casting	Cast-coated Paper		Ink Receptivity
			Surface Strength	Gloss					Surface Strength	Gloss	
Example 33	75	500	10	93	1.75	Comp. Ex. 32	50	510	9	80	1.78
Example 34	75	480	10	93	1.78	Comp. Ex. 33	50	950	10	92	1.75
Example 35	75	560	10	93	1.77	Comp. Ex. 34	45	1200	10	91	1.77
Example 36	75	700	10	93	1.78	Comp. Ex. 35	45	400	6	90	1.76
Example 37	75	440	9.5	92	1.78	Comp. Ex. 36	45	380	3	87	1.78
Example 38	75	400	9	93	1.77	Comp. Ex. 37	40	2300	10	90	1.75
Example 39	75	650	10	92	1.78	Comp. Ex. 38	50	350	4	86	1.78
Example 40	75	400	9	90	1.78	Comp. Ex. 39	40	3000	10	90	1.74
Example 41	70	780	10	93	1.76	Comp. Ex. 40	40	4200	10	88	1.75
Example 42	70	570	10	91	1.78	Comp. Ex. 41	30	5600	10	82	1.78
						Comp. Ex. 42	55	300	5	91	1.73

of methyl methacrylate and, as functional monomers, 2 parts of acrylic acid, 2 parts of acrylamide and 3 parts of hydroxyethyl methacrylate (100 parts of monomers in all) were charged into an autoclave purged with nitrogen gas, followed by polymerizing the monomers at 70° C, stopping the polymerization 15 hours after the initiation of the polymerization at which the degree of polymerization exceeded 98%, cooling the reaction mixture and adjusting pH to 7 with sodium hydroxide to obtain a latex (A). The gel content of the latex was 75% (the latex is hereunder referred to as "latex A-11").

(Preparations of Latex (A) 2 to 6)

Latexes A-12 to A-16 having different gel contents were prepared according to the same procedures and operations as in "Preparation of Latex (A) 1" except for changing the amount of TDM used. The amount of TDM and the gel contents of the resulting latexes (A) are shown in Table IX.

(Preparation of Comparative Latex)

A comparative latex having a gel content of 40% was prepared according to the same procedures and operations as in "Preparation of Latex (A) 1" except for changing the amount of TDM used (the resultant latex will hereunder referred to as "comparative latex a-1").

Table IX

Latex No.	Amount of TDM (parts)	Gel Content (%)
A-11	0.6	75
A-12	1.0	50
A-13	0.8	60
A-14	0.4	85
A-15	0.2	95
a-1	1.2	40

(Preparation of Acrylic Emulsion (B) 1)

Deionized water (120 parts), sodium dodecylbenzenesulfonate (0.1 parts), ammonium persulfate (0.8 parts), divinyl benzene (0.5 parts), and monomer components, i.e., 40 parts of butyl acrylate, 40 parts of styrene, 17 parts of acrylonitrile and 3 parts of methacrylic acid (100 parts of monomers in all) were charged into a three-necked glass reactor purged with nitrogen gas, followed by polymerizing the monomers at 70° C, stopping the polymerization 8 hours after the initiation of the polymerization at which the degree of polymerization exceeded 97%, cooling the reaction mixture and adjusting pH to 7 with an aqueous ammonia solution to obtain an acryl emulsion (B) having a gel content of 75% (the latex will hereunder referred to as "acryl emulsion B-1").

(Preparations of Acrylic Emulsion (B) 2 to 5)

Acryl emulsions B-2 to B-5 having different gel contents were prepared according to the same procedures and operations as in "Preparation of Acryl Emulsion (B) 1" except for changing the amount of divinyl benzene used. The amount of divinyl benzene and the gel contents of the resulting acrylic emulsions (B) are shown in Table X.

(Preparation of Comparative Acrylic Emulsion)

A comparative acrylic emulsion having a gel content of 40% was prepared according to the same procedures and operations as in "Preparation of Acrylic Emulsion (B) 1" except for using 0.2 parts of lauryl mercaptan in place of divinyl benzene (the resultant acrylic emulsion will hereunder be referred to as "comparative acrylic emulsion b-1").

Table X

Acrylic Emulsion No.	Amount of divinyl benzene (parts)	Amount of lauryl mercaptan (parts)	Gel content (%)
B-1	0.5	---	75
B-2	0.1	---	50
B-3	0.3	---	60
B-4	1.0	---	85
B-5	1.5	---	95
b-1	---	0.2	40

(Preparation of Coating Composition)

53.3 Parts of an aqueous casein solution (corresponding to 8 parts expressed in the amount of solid) prepared by heating a mixture of 28% aqueous ammonia (0.8 parts), 8 parts of milk casein and 44.5 parts of water to dissolve these ingredients and 100 parts of water were charged into a Caurex mixer, followed by adding 40 parts of calcium carbonate (TP-222HS; available from OKUTAMA KOGYO CO., LTD.) and 60 parts of kaolin (UW-90; available from EMC) with stirring to admix and disperse the components, adding 3.5 parts (corresponding to 0.7 parts expressed in the amount of solid content) of 20% aqueous solution of calcium acetate and then adding 12 parts (solid content) of the latex A-11 and 7 parts (solid content) of the acrylic emulsion B-1 previously prepared. Finally, the solid content of the paint was controlled to 40% to obtain a paint composition for cast-coated paper according to the present invention.

Examples 44 to 55

Coating compositions were prepared according to the same procedures and operations as in Example 43 except that each combination of one latex selected from the latexes A-11 to A-15 and one acrylic emulsion selected from the acrylic emulsions B-1 to B-5 was substituted for the combination of the latex A-11 and the acrylic emulsion B-1 used in Example 43.

Comparative Examples 43 to 45

Comparative coating compositions were prepared according to the same procedures and operations as in Example 43 except that the latexes and/or the acrylic emulsions whose gel contents were outside the range of this invention were substituted for either or both of the latex A-11 and the acrylic emulsion B-1 used in Example 43. Each combination of these synthetic binders in the comparative paint composition is summarized in Table XI.

Comparative Examples 46 and 47

In these Comparative Examples, there are illustrated experiments in which the latex A-11 and the acrylic emulsion B-1 are separately employed in the paint compositions in order to make the effectiveness of the simultaneous use of these two synthetic binders more clear. In other words, comparative compositions were prepared according to the same procedures and conditions as in Example 43 except that, as shown in Table XI, the latex A-11 and the acrylic emulsion B-1 were separately used in the amount equal to the total amount of these two binders in Example 43.

Test Example

Cast-coated paper was prepared using the paint compositions obtained in the foregoing Examples and Comparative Examples in the same manner as in the aforementioned Test Example and casting speed, permeability, gloss, surface strength and ink receptivity thereof were likewise determined. The results thus obtained are summarized in Table XI given below.

Table XI

Coating Composition	Combination of Synthetic Binders		Casting Speed (m/min.)	Permeability Prior to Casting (sec.)	Cast-Coated Paper	
	Latex	Acrylic Emulsion			Surface Strength	Gloss (%)
Example 43	A-11	B-1	70	1200	10	91
Example 44	A-11	B-2	60	1450	10	90
Example 45	A-11	B-3	65	1350	10	91
Example 46	A-11	B-4	70	1100	9.5	92
Example 47	A-11	B-5	70	1050	9	92
Example 48	A-12	B-1	60	1150	9	92
Example 49	A-13	B-1	65	1250	9.5	91
Example 50	A-14	B-1	70	1200	10	90
Example 51	A-15	B-1	70	1150	10	90
Example 52	A-12	B-2	60	1300	9	92
Example 53	A-13	B-3	65	1250	9.5	91
Example 54	A-14	B-4	70	1100	10	90
Example 55	A-15	B-5	70	1000	10	90
Comp. Ex. 43	A-11	b-1	40	2200	8	85
Comp. Ex. 44	a-1	B-1	45	2400	7	86
Comp. Ex. 45	a-1	b-1	30	4000	4	80
Comp. Ex. 46	A-11	-	35	4600	10	83
Comp. Ex. 47	-	B-1	50	1000	5	91

Claims

1. A paper coating composition for the cast-coating process which comprises mainly a pigment and an adhesive, characterized in that the adhesive comprises, per 100 parts by weight of the pigment, (A) 6 to 18 parts by weight, expressed as solids content, of a latex having an average particle size of 0.1 to 0.3 μm and (B) 3 to 12 parts by weight, expressed as solids content, of a latex or an acrylic emulsion having an average particle size of 0.5 to 1.5 μm , the sum of the solids content of the components (A) and (B) being in the range of 9 to 30 parts by weight.

2. The coating composition according to claim 1 wherein the latexes as the components (A) and (B) are rubber emulsions of polymers having repeating units derived from diene type monomers as essential units.

3. The coating composition according to claim 1 or 2 wherein the acrylic emulsion as the component (B) is an emulsion of polymer having repeating units derived from at least one monomer selected from the group consisting of aromatic alkenyl compounds and mono-olefinic unsaturated compounds as principal repeating units.

5 4. A paper coating composition for the cast-coating process which comprises mainly a pigment and an adhesive, characterized in that the adhesive comprises per 100 parts by weight of the pigment, (A) 2 to 15 parts by weight of casein; (B) 6 to 18 parts by weight, expressed as solids content, of a rubber latex having an average particle size ranging from 0.1 to 0.3 μm ; (C) 3 to 12 parts by weight, expressed as solids content, of an acrylic emulsion or a secondary particle-forming rubber latex having an average particle size
10 ranging from 0.1 to 0.3 μm ; and (D) at least one inorganic compound selected from the group consisting of NaCl, Na₂SO₄, ZnO and MgO and at least one organic acid salt selected from the group consisting of formates and acetates of calcium, zinc and magnesium, the total solid content of the components (A), (B), and (C) being in the range of 18 to 40 parts by weight.

5. The coating composition according to claim 4 wherein the latexes as the components (B) and (C) are
15 a rubber emulsions of polymers having repeating units derived from diene type monomers as essential units.

6. The coating composition according to claim 4 or 5 wherein the acrylic emulsion as the component (C) is an emulsion of a polymer having repeating units derived from at least one monomer selected from the group consisting of aromatic alkenyl compounds and mono-olefinic unsaturated compounds as principal
20 repeating units.

7. The coating composition according to any of the claims 4 to 6 wherein the amount of the component (D) composed of the inorganic and organic compounds to be added to the composition is controlled to such level that the component (C) used as the synthetic binder having a particle size of 0.1 to 0.3 μm is selectively aggregated to form secondary particles and to increase the particle size of the resulting
25 aggregates to 0.5 to 1.5 μm .

8. The coating composition according to claim 7 wherein the amount of the inorganic compound ranges from 0.1 to 7 parts by weight and the amount of the organic acid salt ranges from 0.1 to 3 parts by weight, per 100 parts by weight of the pigment.

9. A paper coating composition for the cast-coating process which comprises mainly a pigment and an
30 adhesive, characterized in that the adhesive comprises a latex (A) having a gel content of not less than 50% and an acrylic emulsion (B) having a gel content of not less than 50%.

10. The coating composition according to claim 9 wherein the amount of the component (A) ranges from 5 to 19 parts by weight and the amount of the component (B) ranges from 3 to 13 parts by weight per 100 parts by weight of the pigment.

35 11. The coating composition according to claim 9 or 10 wherein the latex as the component (A) is a rubber emulsion of a polymer having repeating units derived from diene type monomers as essential repeating units.

12. The coating composition according to any of the claims 9 to 11 wherein the acrylic emulsion as the component (B) is an emulsion of a polymer having repeating units derived from at least one monomer
40 selected from an aromatic alkenyl compound and a mono-olefinic unsaturated compounds as principal repeating units.

13. A cast-coated paper obtained by applying, to the surface of base paper, a coating composition according to any of the claims 1 to 12.

45

50

55

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 331 143 A3

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **89103574.3**(51) Int. Cl.⁵: **D21H 1/22**(22) Date of filing: **01.03.89**

(30) Priority: **02.03.88 JP 47496/88**
02.03.88 JP 47497/88
02.03.88 JP 47498/88
02.03.88 JP 47499/88
02.03.88 JP 47500/88

(43) Date of publication of application:
06.09.89 Bulletin 89/36

(84) Designated Contracting States:
DE FR GB

(88) Date of deferred publication of the search report:
03.04.91 Bulletin 91/14

(71) Applicant: **MITSUI TOATSU CHEMICALS INC.**
No. 2-5, Kasumigaseki 3-chome
Chiyoda-Ku Tokyo 100(JP)

Applicant: **OJI PAPER COMPANY LIMITED**
7-5 Ginza 4-Chome Chuo-ku
Tokyo 104(JP)

(72) Inventor: **Kaneda, Katsumi**
1120, Higashimatano-cho Totsuka-ku
Yokohama-shi Kanagawa(JP)
Inventor: **Hyugaji, Teruo**
3-14-14 Shodo Sakae-ku
Yokohama-shi Kanagawa(JP)
Inventor: **Tanaka, Akio**
21-12, Kamino-cho Sakae-ku
Yokohama-shi Kanagawa(JP)
Inventor: **Kuroda, Nobuo**
1500, Kuzumo
Yonago-shi Tottori(JP)
Inventor: **Yamamoto, Itsuro**
2-20, Tatemachi
Yonago-shi Tottori(JP)
Inventor: **Matsuda, Noriaki**
97-26, Abe
Yonago-shi Tottori(JP)

(74) Representative: **Strehl, Schübel-Hopf,**
Groening
Maximilianstrasse 54 Postfach 22 14 55
W-8000 München 22(DE)

(54) **Coating composition and cast-coated paper coated with same.**

(57) A coating composition for a cast-coated paper which principally comprises a pigment and an adhesive and in which the adhesive is composed of (A) a rubber latex having an average particle size of 0.1 to 0.3 micron and (B) a rubber latex or an acrylic emulsion having an average particle size of 0.5 to 1.5 micron and the sum of the solid content of the components (A) and (B) is in the range of 9 to 30 parts by weight per 100 parts by weight of the pigment is herein provided. The coating composition may further contain casein as a binder. In addition, inorganic compounds selected from NaCl, Na₂SO₄, ZnO and MgO and organic acid salts selected from formates or acetates of Ca, Zn, Mg may be added to the coating composition as coagulants. The use of the aforesaid coating composition makes it possible to produce cast-coated paper having excellent permeability, gloss and surface strength at a high

speed.

EP 0 331 143 A3



European
Patent Office

EUROPEAN SEARCH REPORT

Application Number

EP 89 10 3574

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
A	US-A-4 567 099 (R.L.VAN GILDER ET AL) * claims 1-24 *	1	D 21 H 19/58

A	US-A-4 474 860 (R.L.VAN GILDER ET AL) * claims 1-14 *	1	

			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			D 21 H
The present search report has been drawn up for all claims			
Place of search		Date of completion of search	Examiner
The Hague		01 February 91	FOUQUIER J.P.
CATEGORY OF CITED DOCUMENTS			
X: particularly relevant if taken alone		E: earlier patent document, but published on, or after the filing date	
Y: particularly relevant if combined with another document of the same category		D: document cited in the application	
A: technological background		L: document cited for other reasons	
O: non-written disclosure		-----	
P: intermediate document		&: member of the same patent family, corresponding document	
T: theory or principle underlying the invention			